

09/14/00
Jc922 U.S. PRO

09-15-00

A
Jc682 U.S. PRO
09/661532
09/14/00

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of: Jodi A. Dalvey et al.

Title: IMAGE TRANSFER SHEET

Attorney Docket No.: 946.011US1

PATENT APPLICATION TRANSMITTAL

BOX PATENT APPLICATION

Commissioner for Patents

Washington, D.C. 20231

We are transmitting herewith the following attached items and information (as indicated with an "X"):

☒ Return postcard.

☒ **CONTINUATION-IN-PART (CIP)** of prior Patent Application No. 09/541,874 (under 37 CFR § 1.53(b)) comprising:

☒ Specification (25 pgs, including claims numbered 1 through 21 and a 1 page Abstract).

☒ Informal Drawing(s) (3 sheets).

☒ Unsigned Combined Declaration and Power of Attorney (3 pgs).

The filing fee (NOT ENCLOSED) will be calculated as follows:

	No. Filed	No. Extra	Rate	Fee
TOTAL CLAIMS	21 - 20 =	1	x 9 =	\$9.00
INDEPENDENT CLAIMS	3 - 3 =	0	x 39 =	\$0.00
[] MULTIPLE DEPENDENT CLAIMS PRESENTED				\$0.00
BASIC FEE				\$345.00
TOTAL				\$354.00

THE FILING FEE WILL BE PAID UPON RECEIPT OF THE NOTICE TO FILE MISSING PARTS.

SCHWEGMAN, LUNDBERG, WOESSNER & KLUTH, P.A.
P.O. Box 2938, Minneapolis, MN 55402 (612-373-6900)

By: Jenal M. Kalis
Atty: Jenal M. Kalis
Reg. No. 37,650

Customer Number 21186

"Express Mail" mailing label number: EL576922913US

Date of Deposit: September 14, 2000

This paper or fee is being deposited on the date indicated above with the United States Postal Service pursuant to 37 CFR 1.10, and is addressed to the Commissioner for Patents, Box Patent Application, Washington, D.C. 20231.

IMAGE TRANSFER SHEET

Background of the Invention

5 This application is a Continuation-In-Part of U.S. Application Serial No. 09/541,874, filed April 3, 2000.

The present invention relates to an image transfer sheet capable of image transfer without substantial application of heat, a method for making the image transfer sheet, and a method for transferring an image to a substrate from an image transfer sheet, without a substantial addition of heat.

10 Image transfer to articles made from materials such as fabric, nylon, plastics and the like has increased in popularity over the past decade due to innovations in image development. On February 5, 1974, La Perre issued a United States patent describing a transfer sheet material markable with uniform indicia and applicable to book covers. This sheet material included adhered plies for an ink-
15 receptive printable layer and a solvent-free, heat-activatable adhesive layer. The adhesive layer was somewhat tacky prior to heat activation to facilitate positioning of a composite sheet material on a substrate which was to be bonded. The printable layer had a thickness of 10-500 microns and had an exposed porous surface of thermoplastic polymeric material at least 10 microns thick.

20 Indicia were applied to the printable layer with an old typewriter. A thin film of temperature-resistant, low surface energy polymer, such as polytetrafluoroethylene surface and heated with an iron. Heating caused the polymer in the printable layer to fuse, thereby sealing the indicia into the printable layer.

25 On September 23, 1980, Hare had issued U.S. Patent No. 4,224,358 described a kit for applying a colored emblem to a t-shirt. The kit comprised a transfer sheet which included the outline of a mirror image of a message. To utilize the kit, a user applied a colored crayon to the transfer sheet and positioned the

transfer sheet on a T-shirt. A heated instrument was applied to the reverse side of the transfer sheet in order to transfer the colored message.

The Greenman et al. patent, U.S. Patent No. 4,235,657, issuing November 25, 1980, described a transfer web for a hot melt transfer of graphic patterns onto natural, synthetic fabrics. The transfer web included a flexible substrate coated with a first polymer film layer and a second polymer film layer. The first polymer film layer was made with a vinyl resin and a polyethylene wax which were blended together in a solvent or liquid solution. The first film layer served as a releasable, separable layer during heat transfer. The second polymeric film layer was an ionomer in an aqueous dispersion. An ink composition was applied to a top surface of the second film layer. Application of heat released the first film layer from the substrate while activating the adhesive property of the second film layer, thereby transferring the printed pattern and a major part of the first layer along with the second film layer onto a work piece. The second film layer bonded the printed pattern to the work piece while serving as a protective layer for the pattern.

The Sanders et al. patent, U.S. Patent No. 4,399,209, issuing August 16, 1983, and describes an imaging system in which images were formed by exposing a photosensitive encapsulate to actinic radiation and rupturing the capsules in the presence of a developer so that there was a pattern reaction of a chromogenic material present in the encapsulate or co-deposited on a support with the encapsulate and the developer which yielded an image.

The Goffi patent, U.S. Patent No. 4,880,678, issuing November 14, 1989, describes a dry transfer sheet that comprises a colored film adhering to a backing sheet with an interposition of a layer of release varnish. The colored film included 30-40% pigment, 1-4% of cycloaliphatic epoxy resin, from 15-35% of vinyl copolymer, from 1-4% of polyethylene wax. This particular printing process was described as being suitable for transferring an image to a panel of wood.

1 The Kronzer et al. patent, U.S. Patent No. 5,271,990, issuing
December 21, 1993, describes an image-receptive heat transfer paper that included a
flexible paper-based web sheet and an image-receptive melt transfer film that
overlaid a top surface of the base sheet. The image-receptive melt transfer film was
5 comprised of a thermoplastic polymer melting at a temperature within a range of
65-180°C.

The Higashiyami et al. patent, U.S. Patent No. 5,019,475, issuing
May 28, 1991, describes a recording medium that included a base sheet, a
thermoplastic resin layer formed on at least one side of the base sheet and a color
10 developer layer formed on a thermoplastic resin layer and capable of color
development by reacting with a dye precursor.

Description of the Drawings

Figure 1 illustrates a cross-sectional view of one embodiment of the
15 image transfer sheet of the present invention.

Figure 2 illustrates a cross-sectional view of a base layer-resin layer
combination of one embodiment of the image transfer sheet of the present invention.

Figure 3 illustrates another embodiment of a base layer -- adhesive
layer laminate combination of the image transfer sheet of the present invention.

20 Figure 4 illustrates another embodiment of the image transfer sheet of
the present invention.

Figure 5 illustrates one other embodiment of the image transfer sheet
of the present invention in cross section.

Summary of the Invention

25 One embodiment of the present invention includes an image transfer
sheet. The image transfer sheet comprises an image imparting layer and an adhesive
layer that permits transfer of an image on the image imparting layer to a substrate.

Another embodiment of the present invention includes a kit. The kit comprises an image transfer sheet and a substrate. The image transfer sheet comprises a base layer and an adhesive layer that overlays the base layer.

Another embodiment of the present invention includes a method for
5 transferring an image to a substrate from an image transfer sheet, without an application of heat. The method comprises providing a sheet comprising a base layer and an adhesive layer that overlays the base layer. The sheet has an image. A substrate is provided for receiving the image. The base layer is separated from the adhesive layer. The sheet is contacted to the substrate so that the adhesive layer
10 contacts the substrate, thereby transferring the image to the substrate.

Detailed Description

The image transfer sheet of the present invention, one embodiment of which is illustrated generally at 10 in Figure 1, provides for a transfer of an image
15 from the sheet to a surface such as a T-shirt surface without an application of heat, such as heat from an iron. The image transfer sheet of the present invention 10 comprises a base layer 12, a release layer 14 that overlays the base layer, an adhesive layer 16, such as a PSA adhesive, a polymer layer 18 that overlays the adhesive layer, an optional primer layer 20 for receiving ink that overlays the polymer layer
20 and an optional second ink-receiving layer 22 that overlays the primer or first receiving layer 20. An image or a portion of an image is imparted to one or more of the adhesive layer 16, polymer layer 18, primer layer 20 or optional second ink-receiving layer 22.

As used herein, the term "PVP" refers to poly vinyl pyrolidone.

25 As used herein, the term "AS" refers to acrylo styrene.

As used herein, the term "PA" refers to polyacrylamide.

As used herein, the term "EVA" refers to ethylene vinyl acetate.

As used herein, the term "EAA" refers to ethylene acrylic acid.

As used herein, the term "EMA" refers to ethylene methylacrylate copolymer.

As used herein, the term "MEAA" refers to methane acrylic ethylene acrylate

5 As used herein, the term "PSA" refers to pressure sensitive adhesive.

As used herein, the term "SBR" refers to styrene butadiene resin.

As used herein, the term "Nucrel®" refers to MEAA resin, manufactured by DuPont de Nemours of Wilmington, DE.

As used herein, the term "PVOH" refers to polyvinyl hydroxide.

10 As used herein, the terms "photophopia®" and "Chlorocolor®" and "Chromocolor®" refers to a material that changes color with changes in temperature and changes in light. Photopia is an ink manufactured by Matsui Shikiso Chemical Co. of Kyoto, Japan. "Chromacolor" is a paint manufactured by Chromacolor Intl. Ltd. Of Calgary, AB, CA.

15 As used herein, the term "VA" refers to vinyl acetate.

Weight percentages used herein refer to a dry weight basis.

The image transfer sheet of the present invention accomplishes by the use of an adhesive, such as a PSA adhesive, or hot melt or water-activated adhesive, or a UV cured adhesive, or an electro-beam cured adhesive or an epoxy-based
20 adhesive, what a conventional image transfer layer accomplishes with heat; that is, transfer of an image from the image transfer sheet 10 to a substrate, such as a cloth substrate. Furthermore, the image transfer sheet of the present invention transfers an image that does not substantially fade after repeated washings.

The base layer 12 of the image transfer sheet of the present invention
25 is typically a base paper that has a basis weight of about 15 g/m² to 350 g/m². For some embodiments, the paper basis weight is from about 15 g/m² to 250 g/m². While base weights for paper are described herein, it is understood that, depending upon a particular embodiment, substantially any paper base weight is usable. The base paper is, for some embodiments, coated with clay or a hold-out coating. A

saturated base paper is also usable. The clay coating or hold-out coating is applicable to one side for some embodiments or to both sides for other embodiments.

5 The release layer 14 is typically silicone coated on one side of the release layer or on both sides. Other suitable release coatings usable in the image transfer sheet of the present invention include solid waxes, polyethylene wax, an amide wax, Teflon® powder, a fluorine type release coating, a fluorocarbon release coating, phosphoric acid ester type surfactants and silicone oils.

10 The release coating is prepared, for some embodiments, by dissolving or dispersing in a solvent. The release coating layer may also be prepared by addition to water or solids or by reaction of amino-modified silicone oil or epoxy-modified silicone oil. The release coating is applied to the base paper by any coating method, such as air knife, roll coater, rod and so forth or by extruding or co-extruding with other release layers or by a hot release polymer having an
15 organopolysiloxane component or a lay chain alkyl component in the side chain of the polymer or by using a standard silicone coating water-based solvent. The release coating may also be applied without solvent.

The release coating thickness is between 0.001 and 10 microns. For some embodiments, the release coating thickness is 0.05 to 3 microns.
20 The average release is up to about 2,000 units, as measured by Tessak 12 inches/minute at a specific angle.

For some embodiments, the polymer layer 18 is a polyethylene. The polymer layer is an ink receiving layer. The polymer layer is also an image imparting layer. For some embodiments, the polymer layer has adhesive properties.
25 The polyethylene is extrudable or co-extrudable with another resin with a melt index of about 20 to 3,000, and most preferred, ethylene acrylic acid, EAA, with a melt index from about 2 dg/minute to 3,000 dg/minute as measured by ASTM D- 1238-79. For some embodiments, the melt index is about 10 to 1,500. The vicat

softening point is less than 150 degrees Centigrade. The copolymer may be extruded or coextruded or may exist in solution as a product known as "Nucreal."

The polymer resin, when co-extruded with the release layer, may, for some embodiments be ethylene vinyl acetate, EVA, VA in a percent of 10 to 50%,
5 copolymers which are blended or unblended with a resin tackifier. The polymer resin is blendable with other additives such as a slip agent, an optical brightener, a security feature additive, "GLOW-IN THE DARK" pigments, or color-changeable chemicals with temperature or PHOTOPIA®, with a melt index from 2 dg/minute to 3,000 dg/minute and a vinyl acetate percentage of 0-50%. For some embodiments,
10 the melt index ranges from 8 to 2,500.

The VA % or Surlyn® % ranges from 5-50%. Surlyn® is a ionomer with a melt flow index of about 3 to 100. Surlyn® is manufactured by DuPont de Nemours of Wilmington, DE. One melt index embodiment ranges from about 5 to 20. Other polymers suitable for use in a polymer layer include a polyester adhesive
15 resin having a melting point ranging from 20°C to 300°C and an elongation percent of from 20% to 3,000% at 25°C. Other ethylene acid copolymer resins such as ethylene/methacrylic acid (E/MAA) and ethylene/acrylic acid (E/AA) with an acid content ranging from 2% to 35% and a melt flow index ranging from 2-
2,000 dg/minute are also suitable for use. In one embodiment, the melt index ranges
20 from about 10-700. Other suitable polymers include nylon resin such as polyamide supplied by Societe Nationale Aquitaine (Elf) of Courbevoie, FR, DuPont de Nemours, GMS and Torrey, with or without plasticizer.

The nylon resins are usable with or without plasticizer. Plasticizer is, for some embodiments, added up to a concentration of 50% by weight. Particular
25 embodiments optionally use a plasticizer up to about 30% by weight. The plasticizer is, for some embodiments, blended with a polymer called ENGAGE®, manufactured by Dow Chemical of Midland, MI, and DuPont de Nemours. The ENGAGE® resin is, in some embodiments, blended in a ratio ranging from 95/5 nylon/ENGAGE® to 50/50 nylon/ENGAGE®. The polyamide is, in some

embodiments, blended or coextruded with resins such as EVA or EAA or polyester resin, with or without plasticizers. Plasticizers are added to improve flexibility at concentrations as low as 2% or as high as 27%. One embodiment range is 5% to 20%. The melting temperature is, for some embodiments, less than 150 degrees

5 Centigrade.

For other embodiments, the polymer layer comprises ethylene methylacrylate (EMA) copolymer in a concentration of 0 to 50% methyl acrylic acid and a concentration of 0-35% for some particular embodiments. The EMA includes, in some embodiments, an ester content of 0-50% for some embodiments with an
10 ester concentration of 0 to 40% for particular embodiments.

The polymer layer also includes, for some embodiments, ethylene acrylic ester copolymers or ethylene acrylic ester terpolymers. For other embodiments, the polymer layer includes co-monomers and EMA, ethylene acrylic ester copolymers or ethylene acrylic ester terpolymers in concentrations up to about
15 50%. The melt index of these embodiments in g/10 microns, ranges from 1 to 500, vicat point under 130 degrees Centigrade, and preferably under 90 degrees Centigrade.

Other polymer embodiments include ethylene/acrylic/ester/maleic anhydride termolymers having a vicat temperature that is less than 150 degrees
20 Centigrade and co-monomers in a concentration of 0 to 50%, preferably 0 to 35%. Other polymers include escor acid terpolymers with vicat softening points of less than 150 degrees Centigrade, preferably less than 100 degrees Centigrade. Another polymer includes ethylene n-butyl acrylate with an ester concentration of up to 40%. These polymers are extruded or coextruded as one or multiple layers alone or
25 blended with low density polyethylene, ethylene and vinyl acetate.

Other polymer embodiments include copolymers of ethylene and vinyl acetate that contain up to 50% vinyl acetate by weight with or without additives such as paraffin wax, optical brightener, TiO_2 or TiO_2 xtenders, up to 50% by weight, slip agents, antistatic agents, and so forth, or antioxidants. These co-

polymers have a Melt Index of 1 to 3000 dg/10 min., as measured in ASTM D-1238-79. The copolymers have a Softening point ring and ball of 9 degrees Centigrade, as measured in ASTM E 28-67 (77) from 10 degrees Centigrade to 250 degrees Centigrade.

5 One embodiment of the base layer with a release layer overlay 14 is shown in Figure 2. The base layer for this embodiment 12 is paper or film. This embodiment does not include a release layer or a separate adhesive layer. Instead, the resin layer, which comprises EAA or EVA or a blend of EAA or EVA has adhesive and release properties. Some embodiments have use as a low tack
10 repositionable adhesive.

 To make the image transfer sheet, the release layer and polymer layer may be separately extruded onto the base paper layer or may be co-extruded. The polymer layer is extruded to a thickness of 0.2 mils which is 5 g/m² to 7 mils which is 200 g/m² of one polymer or a blended mix of polymer resin combinations
15 described herein, with or without separate layers of a PSA resin. The polymer is, for some embodiments, coated to a thickness of 0.1 mils or about 2.5 g/m² to 200 g/m². The polymer is co-extruded against the release layer 12.

 The polymer layer 18 is coated with an ink-receiving layer 20. The ink-receiving layer is, for some embodiments, printed with indicia using ink from an
20 ink-jet printer. For other embodiments, indicia are applied with a laser printer or by thermal transfer application. For other embodiments, the polymer layer 18 is not coated with an ink receiving layer. A second ink-receiving layer is optionally coated over the first receiving layer, depending upon the type of final image desired.

 The image transfer sheet is applied to a substrate by separating the
25 polymer and ink-receiving layers and adhesive layer from the base paper and release layer. The adhesive layer contacts the substrate and adheres the polymer and ink-receiving layers to the substrate. In one embodiment, the adhesive layer is a PSA adhesive and has a tackiness that ranges from low to extreme. In an embodiment shown at 50 in Figure 3, an adhesive layer 50 is co-extruded with a base layer to

form a laminate. For low tack embodiments, the layers are removable from articles. Other images may be printed onto the ink receiving layer or layers.

To transfer an image from the image transfer sheet of the present invention 10 to a substrate, the base layer 12 is peeled away from the rest of the sheet. For embodiments such as is shown in Figure 1, the base layer is peeled away at the release layer 14. For embodiments such as is shown in Figure 2, the base layer 12 is peeled at the resin or polymer layer 13.

Separation of the base layer 12 exposes the adhesive layer 16. Once separated and exposed, the adhesive layer 16 is positioned to contact the substrate. Pressure is applied as needed to adhere the image to the substrate. The image has, as discussed, been pre-printed onto the polymer layer 20 and, for some embodiments, has been pre-printed onto a second ink receiving layer. For embodiments with no adhesive, transfer occurs by use of an iron that applies heat to the substrate receiving the image and the image. A heat press is also usable.

Another embodiment of the image transfer sheet of the present invention includes a base layer and a transfer layer that comprises polyamide. Image transfer with this sheet embodiment occurs with low or no addition of heat. The base layer comprises paper or film having a weight of 20 g/m² to 400 g/m². The base layer is fabricated, for some embodiments, with a release coating and for other embodiments, without a release coating.

The polymer transfer layer 18 includes extruded polyamides or a co-extrusion of polyamide--polyamide, polyamide--hot melt polyester resin, polyamide--polyurethane resin, polyamide--adhesive, polyamide--epoxy, especially epoxy with a melting point of 40 degrees C to 300 degrees C and a glass transition of -200 degrees C to a glass transition top of +200 degrees C and an elongation percent of 20% up to about 4000% at 25 degrees C. The polyamide is obtainable from Torray, EF ATO CHEM, EMS and DuPont de Neimours.

Specific materials that could be used include, but are not limited to, H.B. Fuller NP 4038, Bostik Adhesive Polyester 4101, or other grade, or Ricon 131

MA 10, or Poly bd R-45HT Resin and Poly bd 605 resin, other polyamide resin, nylon with or without plasticizer, epoxy or polyurethane. Other resin that is blendable includes ENGAGE®, BYNEL®, modified ethylene acrylic acid terpolymer, EVA, EAA, M/EAA, manufactured by DuPont, polyethylene, epoxy, 5 and polyurethane. Other resins include EMAC, ABAC, which is a Union Carbide EAA ionomer. One other material is a polyamide particle in an EAA solution.

One other material is a urea formaldehyde particle. The urea formaldehyde particle has a high surface area and a size ranging from about 0.1 to 6 microns. The particle has reactive metholyl groups up to about 2% by weight of the particle. One 10 urea formaldehyde particle is manufactured by Markirswerk Co. Of Germany under the name, "Bergopak M2" or "Bergopak M3". Another particle is an aluminum oxide/silica particle. This particle has a surface area of 300 square meters or more. This particle is manufactured by Aluisse of Switzerland, under the name GL1 or GL3, or Martoxilg13.

15 Some embodiments include a plasticizer, such as BBSA, in a concentration of up to 50% by weight, 30% for some embodiments. Other polymers are also usable. A binder such as acrylic, polyethylene wax, polyurethane, EVA, PV OH, PVP, polyamides sol, epoxy, polyester resin, alkyd, solvent or water base or 100% solids is added for some applications.

20 Other additives such as cationic surfactants or dye fixing agents in concentrations up to 70% by weight are added.

The optional ink receptive layer and the polymer transfer layer optionally include pigments such as silica, polyamide particles, titanium oxide, calcium carbonate, zinc sulfate and other pigments in a concentration of up to 100% 25 by weight.

Presented herein are examples of specific embodiments of the image transfer sheet of the present invention. These examples are presented to illustrate particular layers and particular specifications for the layers and are not intended to limit the scope of the present invention.

EXAMPLE 1

One image transfer sheet, illustrated generally at 30 in Figure 4, included a base paper layer 32 with a release layer 34 that overlayed the base paper layer. A PSA adhesive layer 36 overlayed the release layer and an EAA polymer layer 38 overlayed the PSA adhesive layer. The base paper was a 15 g/m² silicone-coated grade from Eastern Fine which was a co-extruded EAA resin with a melt index of about 550 dg/minute. The release layer was co-extruded with pelletized PSA resin HC2278 which was obtained from Fuller with a 2 mil thickness. The EAA polymer was top coated with ink-jet, thermal transfer coating layers. The EAA polymer was printed and was separated from the base layer, and was applied with pressure against a T-shirt without heat. Thicknesses that have been found acceptable for the image transfer sheet include 0.2 mils, 0.5 mils, 0.6 mils, 1 mil, 1.5 mils, 2 mils, 2.5 mils and 3 mils.

EXAMPLE 2

The ink-receiving layer 38 of the example shown in Figure 4 or one or both of ink-receiving layers 20 and 22 of the embodiment shown in Figure 1 were blended with titanium oxide or other pigment in a concentration of up to 60% by weight. Other suitable materials include EAA or EVA with ethylene vinyl acetate. The material has a softness or glass transition temperature of -20 to +30 and an airflex of 111 to 400. The image transfer layer was fabricated as described herein. The image transfer sheet was applied to a dark substrate. In particular, the image transfer sheet was applied to a dark fabric.

EXAMPLE 3

The image transfer sheets shown in Figures 1 and 4 were prepared so that one or more of the image transfer sheet layers were blended with a Glow-in-the-Dark pigment. The Glow-in-the-Dark pigment was added in a concentration of up to 60% by weight of each of the layers. The image transfer sheet was then applied to

a dark fabric substrate. The concentration of Glow-in-the-Dark determines the intensity and duration of the glow. For some embodiments, the glow has a duration of up to 50 hours.

5

EXAMPLE 4

In other embodiments of the image transfer sheet, a changeable color was added to one or more of the layers of the image transfer sheet. The color-changeable material transferred utilized a material such as a chromacolor, a neon light which glows in the dark for over 50 hours depending upon concentration and weight or thickness of neon, and was a phosphorescent pigment, a zinc-oxide pigment or a photochromic light-sensitive colorant. A concentrated batch of one or more of the materials of polyethylene, EVA, EAA, polystyrene, polyamide or MEAA which was a Nucrel®-like material was prepared. The color-changeable material was added to the layer material up to a concentration of 100% by weight with 50% by weight being typical. For some embodiments, the color-changeable material was also added to the ink receiving layer. The color-changeable material technologies changed the image transfer sheet from colorless to one or more of yellow, orange, red, rose, red, violet, magenta, black, brown, mustard, taupe, green or blue. The color-changeable material changed the image transfer sheet color from yellow to green or from pink to purple. In particular, sunlight or UV light or a change in temperature induced the color change.

The color-changeable material was blendable in a batch process with materials such as EAA, EVA, polyamide and other types of resin. The polymer was extruded to 0.5 mils or 14 g/m² to 7 mils or 196 g/m² against a release side or a smooth side for a hot peel with up to 50% by weight of the color-changeable concentrate.

The first ink-receiving layer was an acrylic or SBR EVA, PVOH, polyurethane, MEAA, polyamide, PVP, or an emulsion of EAA, EVA or a blend of EAA or acrylic or polyurethane or polyamide, modified acrylic resins with non-

acrylic monomers such as acrylonitrile, butadiene and/or styrene with or without pigments such as polyamide particle, silica, COCl_2 , titanium oxide, clay and so forth. The ink-receiving layer is capable of receiving ink from printers, lasers, copiers and dye sublimation applications.

5 The thermoplastic copolymer was an ethylene acrylic acid or ethylene vinyl acetate grade, water- or solvent-based, which was produced by high pressure copolymerization of ethylene and acrylic acid or vinyl acetate.

 Using the color-changing material, a binder was additionally added in a concentration of up to 90% with the concentration being up to 73% for some
10 embodiments. The pigment concentration was, for some embodiments, about 50%. The PHOTOPIA® concentration was about 80% maximum. The additive was about 70% maximum. The additive included a pigment or binder. The coating thickness was about 0.1 mils or 2.5 g/m^2 and could have been up to 2 mils or 56 g/m^2 on a dry basis.

15 The second receiving layer included the PHOTOPIA® material in a concentration of up to 70% by weight with a range of 2 to 50% by weight for some embodiments. The pigment ranged from 0 to 90% and the binder from 0 to 80%. This type of coloring scheme was used in shirts with invisible patterns and slogans. The PHOTOPIA® products were obtained from Matsui International Company, Inc.
20 While they have been described as being incorporated in the ink-receiving layer, the PHOTOPIA® products were also applicable as a separate monolayer. PHOTOPIA®-containing layers were coated onto the release layer by conventional coating methods such as by rod, slot, reverse or reverse gravure, air knife, knife-over and so forth.

25 Chromacolor materials could also be added to the image transfer sheet. Chromacolor materials changed color in response to a temperature change. The chromocolor solid material had a first color at a first temperature and changed color as the temperature changed. For instance, solid colors on a T-shirt became colorless as a hot item or the outside temperature increased.

Chromacolor was prepared as a polypropylene concentrate, polyethylene, polystyrene, acrylo-styrene (AS) resins, PVC/plasticizer, nylon or 12 nylon resin, polyester resin, and EVA resin. The base material for this image transfer sheet embodiment was selected from materials such as paper, PVC, 5 polyester, and polyester film.

This type of image transfer sheet was fabricated, in some embodiments, without ink-jet receiving layers. It was usable by itself for color copy, laser printers, and so forth and then was transferable directly onto T-shirts or fabrics.

In one or both receiving layers, permanent color was addable with a 10 color-changeable dispersion when the temperature changed, that is, when color disappeared. The color returned to permanent color as was shown in previous examples. With this formulation, the changeable color was added to one or more layers in a concentration of up to about 80% by weight with a range of 2-50% by weight being typical. The base paper for this embodiment was about 90 g/m². 15 About 0.5 mils EAA were applied with 10% PHOTOPIA® or temperature-sensitive color-changeable materials. The top coat layer was an ink-receiving layer that contained polyamides, silica, COCl₂ for 15% color-changeable items.

This embodiment is usable in conjunction with conventional printing technology, laser imaging, color copies, and die sublimation applications. 20

EXAMPLE 5

An EVA DuPont 3180 or 3185 with or without a co-extruded layer of Surlyn® 1702, obtained from DuPont, was employed as the polymer layer. The remaining image transfer sheet was as described in Figures 1 and 4. PSA was usable 25 for a cold transfer or for use with an iron or heat press transfer or other type of heat activation at 55 to 160 degrees.

EXAMPLE 6

Another embodiment of the image transfer sheet of the present invention was shown at 40 in Figure 5. This image transfer sheet included a base layer 42 that included a paper. The paper had a base weight which was 90 g/m² silicone coated with 100 g of release layer material 44. An adhesive layer 46 was a co-extruded layer of 1.5 mils polyester, 0.75 mils polyamide, and 1.5 mils HB Fuller adhesive. An ink-jet receiving layer was applied with or without a color-changeable chemical or Glow-in-the-Dark chemical or dark fabric transfer.

EXAMPLE 7

Polyamides were extruded or co-extruded to a density of 5 g/m² or 0.2 mils to 200 g/m² or 7.00 mils. The polyamide was either pigmented or non-pigmented. Pigments were added in concentrations up to about 50% and included titanium oxide, calcium carbonate and so forth. Other additives included an optical brightener, a slip agent, a wax additive and an antioxidant, Glow in the Dark pigments, color changeable by heat or light or fluorescent colors. The polyamides with additives were added to 0.5 mils or 14 g/m² to 136 g/m² or 6 mils.

EXAMPLE 8

A release base paper was silicone coated to 90 g/m². Polyamide was overlaid onto the base layer by extrusion or co-extrusion to a thickness of 1.5 mils. Polyamide was M548, manufactured by ELF. The polyamide layer was coated with an inkjet premium receiving layer which was transferred at 160 degrees F, 175 degrees F, 200 degrees F, 250 degrees F, 300 degrees F, 400 degrees F, 450 degrees F. The image transfer sheet displayed excellent transfer with substantially no yellowness. Transferred images had an excellent washability at 40 degrees C.

EXAMPLE 9

The procedure described in Example 7 was employed with a Bostik Polyester 4101. Image transfer was performed at about 200 degrees F or higher. The transferred image displayed no yellowness, an excellent transfer, and no
5 cracking.

EXAMPLE 10

Polyamide and/or polyester and/or EVA were extruded or co-extruded with an adhesive layer against release paper to make an image transfer
10 layer. An inkjet receiving coating layer was then applied. The ink receiving layer was printed with an HP 890 printer. Pressure was applied to permit image transfer. The transferred image displayed an excellent adhesion to fabric and an excellent washability.

EXAMPLE 11

An image transfer sheet was made in a manner described in Example 10. Additionally, pigment was added to the image transfer layer and optionally the
15 ink receiving layer. The pigment was a "Glow in the Dark" pigment with a concentration of up to 60% by weight. Other pigments optionally added included
20 color changeable materials, light changeable materials, and dark transfer materials.

EXAMPLE 12

A release base paper of 90 g/m² was provided. The release paper was co-extruded to 1.75 mils with polyamide and to 0.75 mils with polyester Bostik
25 4101. The co-extruded product was top coated with one or more inkjet receiving layers.

EXAMPLE 13

An image transfer sheet was prepared as described for Example 12 except that 1.5 mils of polyester resin were co-extruded with 0.75 mils of polyamide. The product had an excellent laser, color copy and transfer.

5

EXAMPLE 14

The image transfer sheet of Example 12 was prepared with a use of plasticizer polyamides and about 15% plasticizer.

10

EXAMPLE 15

The image transfer sheet of Example 12 was prepared with a use of 1.2 mils EAA co-extruded with 0.75 mils of polyamide.

EXAMPLE 16

15 The image transfer sheet of Example 12 was prepared with a use of 1.5 mils EVA DuPont 3180 and 0.75 mils polyamides.

EXAMPLE 17

20 The image transfer sheet of Example 12 was prepared with a use of 2 mils polyamide ELF and 1 mil of EAA, 20% acrylic acid.

EXAMPLE 18

25 The image transfer sheet of Example 12 was prepared with a use of 1.5 mils EVA, a modifier with wax and DuPont 3200-2 and 1.0 mils EAA.

EXAMPLE 19

The image transfer sheet of Example 12 was prepared with a use of a second polyester layer that had a melt point of 127 degrees C; a melt point viscosity of 192,000 at 180 degrees C and an elongation of 490% at 25 degrees C. The first
5 EAA layer was 1.25 mils. The second polyester layer was 0.75 mils.

EXAMPLE 20

A 50/50 EAA/PE polymer with a melt point of 120 degrees C was extruded against a release and base layer to 2 mils. The polymer was coated with an
10 ink jet receiving layer or layers to make an image transfer sheet. The image transferred displayed excellent washability and softness.

All examples were tested for laser transfer without ink jet receiving layers and displayed good to excellent color retention.

EXAMPLE 21

One or more layers of EMA are extruded or co-extruded to a thickness of about 12 microns to about 220 microns. The extruded layer or layers may be EMA alone. For some embodiments, the extruded layer or layers may be
15 EMA with a concentration of up to about 50% by weight, titanium oxide extenders.
20 For other embodiments, the extruded layer or layers comprise EMA with a Glow in the Dark pigment.

EXAMPLE 22

One or more of the following materials are blended to make a
25 polymer layer: EMA and EAA; EMA and EVA; EMA and EVA and EAA; EMA and polyester resin; EMA and nylon; EMA and low density polyethylene for one layer. This layer is overlaid with polymer layers that comprise titanium oxide or titanium oxide extenders in concentrations up to 30%.

EXAMPLE 23

The following materials are mixed and coextruded to form the following layers:

- An EMA layer having a thickness of 25 microns and 0.5 mils of Surlyn;
- 5 An EMA layer having a thickness of 50 microns and 0.75 mils of Surlyn;
- and

An EMA layer having a thickness of 100 microns and 0.5 mils of Surlyn.

- This coextrusion is repeated with EAA and EVA. For some embodiments, EVA is used alone, in place of the EMA. For other embodiments, EAA is used
- 10 alone, in place of EMA to make layers having thicknesses described for EMA. It has surprisingly been found that EMA provides a softer handling product while still providing excellent washability.

EXAMPLE 24

- 15 The following materials are mixed and coextruded to form the following layers:

- An EMA blend with polyamide; a mixture of EMA and EVA; EMA and EVA coextruded at rates of 1-20 and 20-1. These layers are adhered with a PSA adhesive. These layers overlay an ink jet receiving layer. The ink jet receiving layer
- 20 comprises a polyacetate polymer in an EA solution with or without vinyl acetate polymer. This material has a soft feel.

- For some embodiments transferring an image to a dark substrate, the ink receiving layer includes ash titanium in a concentration of 30%. For other embodiments, titanium oxide is blended in a ratio of 3:2 titanium oxide to polymer
- 25 such as M 2 Bergopak. For some embodiments titanium oxide is added to top layers and Glow- In- The- Dark pigment is added to lower layers in a concentration of about 3%. For other embodiments, a white layer is prepared by blending EA with Airflux 110.

EA is dissolved and mixed with Ergosol, latex, Airflux and cationic resin to form a mixture. The mixture is applied to the surface of release paper without extrusion. For some embodiments, the mixture is applied to the ink jet receiving layer.

5 Although the present invention has been described with reference to particular embodiments, workers skilled in the art will recognize that changes may be made in form and detail without departing from the spirit and scope of the invention.

10

15

In the Claims

1. An image transfer sheet, comprising: an image imparting layer comprising an ethylene copolymer.
- 5 2. The image transfer sheet of claim 1 and further comprising an adhesive layer that permits transfer of an image of the image imparting layer to a substrate.
3. The image transfer sheet of claim 1 wherein the ethylene copolymer is
10 ethylene methylacrylate.
4. The image transfer sheet of claim 1 wherein the ethylene copolymer is ethylene acrylic ester copolymer.
- 15 5. The image transfer sheet of claim 1 wherein the ethylene copolymer is ethylene acrylic ester terpolymer.
6. The image transfer sheet of claim 1 wherein the image imparting layer overlays the adhesive layer.
- 20 7. The image transfer sheet of claim 1 and further comprising a release layer that underlay the adhesive layer.
8. The image transfer sheet of claim 1 and further comprising a primer layer
25 that overlays the polymer layer.
9. The image transfer sheet of claim 1 and further comprising a second image imparting layer that overlays the primer layer.

10. The image transfer sheet of claim 1 wherein the image imparting layer has adhesive properties.

11. The image transfer sheet of claim 10 wherein the image imparting layer has
5 release properties.

12. The image transfer sheet of claim 10 wherein the image imparting layer comprises one or more of ethylene methacrylate copolymer in a concentration of up to about 50% by weight methyl acrylic acid; ethylene acrylic ester copolymer;
10 ethylene acrylic ester terpolymer; ethylene/acrylic ester/maleic anhydride terpolymer and co-monomer; Escor acid terpolymers; or ethylene n-butyl acrylate.

13. The image transfer sheet of claim 1 and further comprising a base layer that supports the adhesive layer and the image imparting layer.
15

14.. The image transfer sheet of claim 13 wherein the base layer and the adhesive layer are laminated.

15. The image transfer sheet of claim 1 wherein the image imparting layer
20 comprises coloring agents.

16. The image transfer sheet of claim 15 wherein the coloring agents change color with changes in temperature or with changes in pH.

25 17. A kit comprising :
an image transfer sheet comprising a base layer and an adhesive layer that overlays the base layer wherein the base layer comprises an ethylene copolymer; and
a substrate that receives an image from the image transfer sheet.

18. The kit of claim 17 and further comprising a container for containing the image transfer sheet and the substrate.

19. The kit of claim 17 wherein the substrate is selected from the group
5 consisting of a -shirt, towels, clothing, sheets, and napkins.

20. An image transfer layer comprising an image imparting layer, the image
imparting layer comprising co-extruded layers of ethylene methylacrylate
copolymers and Surlyn.

10

21. The image transfer layer of claim 20 and further comprising nylon.

15

20

25

ABSTRACT

The present invention includes an image transfer sheet. The image transfer sheet includes an image imparting layer and an adhesive layer. The
5 adhesive layer permits transfer of an image to a substrate.

"Express Mail" mailing label number: EL576922913US

Date of Deposit: September 14, 2000

This paper or fee is being deposited on the date indicated above with the United States Postal Service pursuant to 37 CFR 1.10, and is addressed to the Commissioner for Patents, Box Patent Application, Washington, D.C. 20231.

004760" 2222222222




Fig. 1





Fig. 2

09661532 091400



77.5

SCHWEGMAN • LUNDBERG • WOESSNER • KLUTH

United States Patent Application

COMBINED DECLARATION AND POWER OF ATTORNEY

As a below named inventor I hereby declare that: my residence, post office address and citizenship are as stated below next to my name; that

I verily believe I am the original, first and joint inventor of the subject matter which is claimed and for which a patent is sought on the invention entitled: **IMAGE TRANSFER SHEET**.

The specification of which is attached hereto.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with 37 C.F.R. § 1.56 (attached hereto). I also acknowledge my duty to disclose all information known to be material to patentability which became available between a filing date of a prior application and the national or PCT international filing date in the event this is a Continuation-In-Part application in accordance with 37 C.F.R. § 1.63(e).

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on the basis of which priority is claimed:

No such claim for priority is being made at this time.

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States provisional application(s) listed below:

No such claim for priority is being made at this time.

I hereby claim the benefit under 35 U.S.C. § 120 or 365(c) of any United States and PCT international application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT international application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose material information as defined in 37 C.F.R. § 1.56(a) which became available between the filing date of the prior application and the national or PCT international filing date of this application:

Application Number
09/541,874

Filing Date
April 3, 2000

Status
Pending

I hereby appoint the following attorney(s) and/or patent agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected herewith:

Anglin, J. Michael	Reg. No. 24,916	Huebsch, Joseph C.	Reg. No. 42,673	Nelson, Albin J.	Reg. No. 28,650
Bianchi, Timothy E.	Reg. No. 39,610	Jurkovich, Patti J.	Reg. No. 44,813	Nielsen, Walter W.	Reg. No. 25,539
Billion, Richard E.	Reg. No. 32,836	Kalis, Janal M.	Reg. No. 37,650	Oh, Allen J.	Reg. No. 42,047
Black, David W.	Reg. No. 42,331	Kaufmann, John D.	Reg. No. 24,017	Padys, Danny J.	Reg. No. 35,635
Brennan, Leoniede M.	Reg. No. 35,832	Klima-Silberg, Catherine I.	Reg. No. 40,052	Parker, J. Kevin	Reg. No. 33,024
Brennan, Thomas F.	Reg. No. 35,075	Kluth, Daniel J.	Reg. No. 32,146	Perdok, Monique M.	Reg. No. 42,989
Brooks, Edward J., III	Reg. No. 40,925	Lacy, Rodney L.	Reg. No. 41,136	Prout, William F.	Reg. No. 33,995
Chu, Dinh C.P.	Reg. No. 41,676	Lemaire, Charles A.	Reg. No. 36,198	Schumm, Sherry W.	Reg. No. 39,422
Clark, Barbara J.	Reg. No. 38,107	LeMoine, Dana B.	Reg. No. 40,062	Schwegman, Micheal L.	Reg. No. 25,816
Clise, Timothy B.	Reg. No. 40,957	Lundberg, Steven W.	Reg. No. 30,568	Scott, John C.	Reg. No. 38,613
Dahl, John M.	Reg. No. 44,639	Maeyaert, Paul L.	Reg. No. 40,076	Smith, Michael G.	Reg. No. 45,368
Drake, Eduardo E.	Reg. No. 40,594	Maki, Peter C.	Reg. No. 42,832	Speier, Gary J.	Reg. No. 45,458
Embretson, Janet E.	Reg. No. 39,665	Malen, Peter L.	Reg. No. 44,894	Steffey, Charles E.	Reg. No. 25,179
Fordenbacher, Paul J.	Reg. No. 42,546	Mates, Robert E.	Reg. No. 35,271	Terry, Kathleen R.	Reg. No. 31,884
Forrest, Bradley A.	Reg. No. 30,837	McCrackin, Ann M.	Reg. No. 42,858	Tong, Viet V.	Reg. No. 45,416
Gamon, Owen J.	Reg. No. 36,143	Moore, Charles L., Jr.	Reg. No. 33,742	Viksins, Ann S.	Reg. No. 37,748
Harris, Robert J.	Reg. No. 37,346	Nama, Kash	Reg. No. 44,255	Woessner, Warren D.	Reg. No. 30,440

I hereby authorize them to act and rely on instructions from and communicate directly with the person/assignee/attorney/firm/organization/who/which first sends/sent this case to them and by whom/which I hereby declare that I have consented after full disclosure to be represented unless/until I instruct Schwegman, Lundberg, Woessner & Kluth, P.A. to the contrary.

Please direct all correspondence in this case to **Schwegman, Lundberg, Woessner & Kluth, P.A.** at the address indicated below:
P.O. Box 2938, Minneapolis, MN 55402
Telephone No. (612)373-6900

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of joint inventor number 1 : **Jodi A. Dalvey**
Citizenship: **United States of America** Residence: **Orono, MN**
Post Office Address: **3230 Bohns Point Lane**
Orono, MN 55331

Signature: _____
Jodi A. Dalvey

Date: _____

Full Name of joint inventor number 2 : **Nabill F. Nasser**
Citizenship: **United States of America** Residence: **Minneapolis, MN**
Post Office Address: **121 South Washington, No. 1106**
Minneapolis, MN 55401

Signature: _____
Nabill F. Nasser

Date: _____

§ 1.56 Duty to disclose information material to patentability.

(a) A patent by its very nature is affected with a public interest. The public interest is best served, and the most effective patent examination occurs when, at the time an application is being examined, the Office is aware of and evaluates the teachings of all information material to patentability. Each individual associated with the filing and prosecution of a patent application has a duty of candor and good faith in dealing with the Office, which includes a duty to disclose to the Office all information known to that individual to be material to patentability as defined in this section. The duty to disclose information exists with respect to each pending claim until the claim is canceled or withdrawn from consideration, or the application becomes abandoned. Information material to the patentability of a claim that is canceled or withdrawn from consideration need not be submitted if the information is not material to the patentability of any claim remaining under consideration in the application. There is no duty to submit information which is not material to the patentability of any existing claim. The duty to disclose all information known to be material to patentability is deemed to be satisfied if all information known to be material to patentability of any claim issued in a patent was cited by the Office or submitted to the Office in the manner prescribed by §§ 1.97(b)-(d) and 1.98. However, no patent will be granted on an application in connection with which fraud on the Office was practiced or attempted or the duty of disclosure was violated through bad faith or intentional misconduct. The Office encourages applicants to carefully examine:

- (1) prior art cited in search reports of a foreign patent office in a counterpart application, and
- (2) the closest information over which individuals associated with the filing or prosecution of a patent application believe any pending claim patentably defines, to make sure that any material information contained therein is disclosed to the Office.

(b) Under this section, information is material to patentability when it is not cumulative to information already of record or being made of record in the application, and

- (1) It establishes, by itself or in combination with other information, a prima facie case of unpatentability of a claim; or
- (2) It refutes, or is inconsistent with, a position the applicant takes in:
 - (i) Opposing an argument of unpatentability relied on by the Office, or
 - (ii) Asserting an argument of patentability.

A prima facie case of unpatentability is established when the information compels a conclusion that a claim is unpatentable under the preponderance of evidence, burden-of-proof standard, giving each term in the claim its broadest reasonable construction consistent with the specification, and before any consideration is given to evidence which may be submitted in an attempt to establish a contrary conclusion of patentability.

(c) Individuals associated with the filing or prosecution of a patent application within the meaning of this section are:

- (1) Each inventor named in the application;
- (2) Each attorney or agent who prepares or prosecutes the application; and
- (3) Every other person who is substantively involved in the preparation or prosecution of the application and who is associated with the inventor, with the assignee or with anyone to whom there is an obligation to assign the application.

(d) Individuals other than the attorney, agent or inventor may comply with this section by disclosing information to the attorney, agent, or inventor.